



SPECIFICATIONS AND PRICING

PE LC-300 foam sheet

Physical Properties

Type.....	Open Cell
Polymer.....	PE
Colors.....	Grey
1. 50% Compression Resistance (psi).....	26.25 Min
2. 50% Compression set (%).....	1.4
3. Density (lb/ft. ³).....	2.12
4. Tensile (psi).....	16 Min
5. Elongation (%).....	180 Min
6. Flammability.....	UL HF-1 grade

Standard bun size: 3 inch x 36 inch x 72 inch