



PREMLENE™ HIGH TENSILE EPDM RUBBER SHEET EPS-PSS-B60

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	60 ± 5	Shore A Durometer	D2240
Tensile Strength	1200	PSI	D412
Elongation	300	%	D412
Compression Set	50%	22 hours @ 70 ° C	D395B
Tear Value	110	PLI	
Lowest Working Temp.	-22 ° F		
Highest Working Temp.	212 ° F		

Heat Aging

Heat resistance after 70 hours @ 100 ° C			D573
Change in Hardness	10	%	
Change in Tensile	-20	%	
Change in Elongation	-60	%	

Product Range

Colour: **BLACK**

Thickness: 0.8 mm - 9.5 mm (1/32" - 3/8")

Length: 33' - 66'

Width: 36" - 48"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

PATTERN:

Smooth both sides

Fabric finish one side 2.5% up-charge

Fabric finish one side 5% up-charge

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Volume 1
Version 1
April 2008