



**PREMLENE™ NATURAL RUBBER SHEET
(PURE GUM)
GMS-SS-N35/GMS-SS-T35/GMS-SS-R35**

Test	Typical Value	Units	ASTM Method
Hardness	35 ± 5	Shore "A" Durometer	D2240
Tensile Strength	2300	PSI	D412
Elongation	650	%	D412
Lowest Working Temp.	-40 ° F		
Highest Working Temp.	158 ° F		
<u>Heat Aging</u>			D573
Heat resistance after 70 hours @ 100 ° C			
Change in Hardness	+4	%	
Change in Tensile	-45	%	
Change in Elongation	-28	%	

Product Range

Colour: **NATURAL, TAN & RED**,

Thickness: 0.8 mm - 50.8 mm (1/32" - 2")

Length: 17' - 66'

Width: 4" - 48"

Width Tolerance:

48" widths ± .177"

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

1/2" ± .047"

3/4" ± .094"

1" ± .100"

1 1/4" ± .110"

1 1/2" ± .114"

Pattern: Smooth both sides, fabric finish one side

Fabric finish one side 2.5% up-charge.

Fabric finish both sides 5% up-charge.

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Volume 1

Version 1

September 2005