



PREMLENE™ HYPALON RUBBER SHEET HYS-SS-B60

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	60 ± 5	Shore A Durometer	D2240
Tensile Strength	1100	PSI	D412
Elongation	300	%	D412
Compression Set	30%	22 hours @ 70? ° C	D395B
Tear Value	165	PLI	
Lowest Working Temp.	-22 ° F		
Highest Working Temp.	248 ° F		

Heat Aging

Heat resistance after 70 hours @ 100 ° C			D573
Change in Hardness	6	%	
Change in Tensile	-30	%	
Change in Elongation	-50	%	

Product Range

Colour: **BLACK**

Thickness: 0.8 mm - 9.5 mm (1/32" - 3/8")

Length: 17' - 100'

Width: 36" - 48"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

Pattern:

Smooth both sides

Fabric finish one side 2.5% up-charge

Fabric finish one side 5% up-charge

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Volume 1
Version 1
February 2007