



## PREMLENE™ ECONOMY GRADE NEOPRENE SHEET NES-ESS-B40

| Test              | Typical Value | Units                  | ASTM Method |
|-------------------|---------------|------------------------|-------------|
| Hardness          | 40 ± 5        | Shore "A"<br>Durometer | D2240       |
| Tensile Strength  | 350           | PSI                    | D412        |
| Elongation        | 300           | %                      | D412        |
| Oil Swell: #3 Oil | 120%          | 22 hours @ 70 ° C      |             |

### Product Range

Colour: **Black**

Thickness: 0.8 mm - 50.8 mm (1/32" - 2")

Length: 17' - 250'

Width: 4" - 72"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

1/2" ± .047"

3/4" ± .094"

1" ± .100"

1 1/4" ± .110"

1 1/2" ± .114"

Pattern: Smooth both sides, fabric finish one side

**Fabric finish one side 2.5% up-charge**

**Fabric finish both sides 5% up-charge**

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: [sales@gcpelastomeric.com](mailto:sales@gcpelastomeric.com)

Web: [www.gcpelastomeric.com](http://www.gcpelastomeric.com)

Volume 1  
Version 1  
May 2005