



PREMLENE™ BLACK NITRILE SHEET NIS-SS-B50

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	50 ± 5	Shore A Durometer	D2240
Tensile Strength	650	PSI	D412
Elongation	300	%	D412

Oil Swell

#3 Oil 70 Hours @ 70 ° C 90% Max

Product Range

Colour: **BLACK**

Thickness: 1.6 mm - 12.7 mm (1/32" - 2")

Length: 17' - 66'

Width: 36" - 48"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

1/2" ± .047"

Pattern: Smooth both sides

Fabric finish one side 2.5% up-charge

Fabric finish one side 5% up-charge

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Volume 2
Version 1
March 2006