

## PREMLENE<sup>TM</sup> NEOPRO<sup>TM</sup> ORS-SS-B60/ORS-SS-B70

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	60 & 70 ± 5	Shore A Durometer	D2240
Tensile Strength	770	PSI	D412
Elongation	300	%	D412
Tear Value	14.3	KN/M	
<b>OR</b>			
Compression Set	31%	22 hours @ 70 ° C	D395B
Oil Aging	ASTM	#3 Oil	D471
<u>Change in Volume</u>	<=60	22 hours @ 100 ° C	D573

### Product Range

Colour: **BLACK**

Thickness: 0.8 mm - 50.8 mm (1/32" - 2")

Length: 17' - 150'

Width: 36" - 48"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

1/2" ± .047"

3/4" ± .094"

1" ± .100"

1 1/4" ± .110"

1 1/2" ± .114"

Pattern: Smooth both sides

**Fabric finish one side 2.5% up-charge**

**Fabric finish one side 5% up-charge**