



PREMLENE™ OIL RESISTANT RUBBER SHEET ORS-SS-B50

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	50 ± 5	Shore A Durometer	D2240
Tensile Strength	750	PSI	D412
Elongation	400	%	D412
Compression Set	32%	22 hours @ 70 ° C	D395B
Oil Aging	ASTM	#3 Oil	D471
Change in Volume	<=60	22 hours @ 100 ° C	D573

Product Range

Colour: **BLACK**

Thickness: 0.8 mm - 50.8 mm (1/32" - 2")

Length: 17' - 150'

Width: 4" - 72"

Width Tolerance:

48" widths ± .177",

All other widths ± .063"

Gauge Tolerance:

1/8", 1/4", 3/8" ± .032

1/2" ± .047"

3/4" ± .094"

1" ± .100"

1 1/4" ± .110"

1 1/2" ± .114"

Pattern: Smooth both sides

Fabric finish one side 2.5% up-charge

Fabric finish one side 5% up-charge

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Volume 2
Version 1
February 2004