



PREMLENE™ FLUROELASTOMER RUBBER

VIS-SS-B70

TEST	TYPICAL VALUE	UNITS	ASTM METHOD
Hardness	70 ± 5	Shore A Durometer	D2240
Tensile Strength	1100	PSI	D412
Elongation	200	%	D412
Lowest Working Temp	-122 ° F (-86 ° C)		
Highest Working Temp	356 ° F (179 ° C)		

Product Range

Colour: **BLACK**

Thickness: 1.6 mm - 6.4 mm (1/16" - 1/4")

Length: 33' - 50'

Width: 48"

Width Tolerance:

48" widths ± .177"

Gauge Tolerance:

1/8", 1/4" ± .032

Pattern: Smooth both sides

Fabric finish one side 2.5% up-charge

Fabric finish one side 5% up-charge

170 Webster Road, Kitchener, ON, Canada N2C 2E6 Phone: 519-893-8207 Fax: 519-893-9356

Email: sales@gcpelastomeric.com

Web: www.gcpelastomeric.com

Version 1
Volume 2
March 2005